

U-POL[®]

REFACE

Polyester Spray Putty

Description

U-POL REFACE is a highly effective two component spray putty for the preparation of irregular steel and fiber glass surfaces. **U-POL REFACE** gives a very high build, adheres excellently to metal and is easy to sand and is the ideal base for most paint systems.

Health and Safety Statement

FOR PROFESSIONAL USE ONLY. Read full instructions before use.
IMPORTANT: This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at WWW.U-POL.COM. U-POL disclaim any liability where the user does not wear the recommended personal protective equipment.

Surface preparation and instructions for use

U-POL REFACE can be applied to the following -

- Bare metal. (*)
- Polyester putties and bodyfillers.
- Fully cured paint surfaces.

* Note: REFACE is not recommended for use over Aluminum, Galvanized (Zinc coated) or etch primers.

Thoroughly clean and degrease surfaces with a suitable spirit wipe or thinner. Sand with 80 grit paper for bare metal or 220 grit for painted surfaces.
Re-clean and dry.

Hardener

Mix **U-POL REFACE** and hardener thoroughly. Add hardener at 5 parts per 100 by volume or 3% by weight. Only mix amount required for immediate work. Never return unused mixed product to the can.

Application

Stir well before use. Minimum recommended working temperature is 50°F. Application with a gravity fed gun is preferable, though a suction gun will suffice. Use a 2mm-3mm fluid tip. Hold gun 6-8 ins from panel. Layers may be built up wet on wet, but 5-10mins. Between coats is recommended.

Pot life

20-30 minutes at 70°F

Thinners

Thinning is not recommended. Use lacquer thinners or similar proprietary products to clean gun.

Build and pressure

2-3 spray cycles of several layers will give a very high build. Each pass will give a build of approximately 3-4 thou. A pressure of 40-50 p.s.i. required at the gun.

Drying time

2-3 hours at 70°F or 30 mins at 140°F. Drying time is dependent upon film thickness, humidity and temperature.

Over-painting

Dry sand, clean and dry thoroughly, **U-POL REFACE** may then be overcoated with most primers and paint systems. A non sanding sealer is necessary if used in damp climatic conditions.

Product codes

UP719 - 1L can
UP733 - 2.5L can

U-POL US, Inc., 630 Selvaggio Dr, Suite 300, Nazareth, PA 18064

Tel: (800) 340 7824; Fax: (800) 787 5150

Email: sales-us@u-pol.com Website: www.u-pol.com