



RUST PREVENTER

TECHNICAL DATA SHEET

Description

3957() RUST PREVENTER is a non-hardening internal panel compound to replace OEM corrosion protection on inner body panels. It is semi-transparent black in color and is easily applied to inner panels with a 360° pattern using the **71110 PREMIUM UNDERCOAT GUN & WAND** or the **71120 RUST PREVENTER AEROSOL WAND**. It's fast drying formula is a simple way to restore corrosion protection on new parts and replacement panels.

Features

- **Non-hardening**
- **Fast drying**
- **Corrosion protection**
- **Black Color**

Typical Properties

Container	<u>39573</u>	<u>39574</u>
Color	24 oz aerosol	Quart bottle
VOC (regulatory)	Transparent Black	Transparent Black
VOC (actual)	NA	3.58 #/gl (430 g/l)
MIR	NA	3.53 #/gl (424 g/l)
Paintable	.812	NA
	No	No

Handling and Application

PREPARATION: Clean surface with **3837() SEM SOLVE** or compliant cleaner.

APPLICATION: **39573 Aerosol**
Shake can for 1 minute prior to use. Remove cap, attach straw or tip with wand.

NOTE: With the wand attached, the spray pattern is 360° so do not spray product without wand being inserted into inner panel access point.

Apply 1-2 coats. If using the wand, change the angle of the wand, and vary the depth of the wand inside the panel to ensure complete coverage. Clean wand by attaching the tip and wand to **77743 XXX GUN CLEANER** or solvent compliant in your area.

39574 Quart
Shake bottle for 1 minute prior to use, remove cap. Attach **39574** to **71110 PREMIUM UNDERCOAT GUN & WAND**.

NOTE: With the wand attached, the spray pattern is 360° so do not spray product without wand being inserted into inner panel access point.

Using 35-40 psi, apply 1-2 coats changing the angle of the gun, and varying the depth of the wand inside the panel to ensure complete coverage. Allow 2-3 minutes flash time between coats. Clean wand with **77743 XXX GUN CLEANER** or solvent compliant in your area.

STORAGE:

3957() RUST PREVENTER should be stored in a cool dry place with adequate ventilation away from heat, sparks and flames. The shelf life for **3957()** is 3 years when stored under normal conditions.

TECHNICAL CONSULTATION SERVICE

Our Technical Staff is ready to assist you with any questions. You are invited to take advantage of our extensive experience, laboratory services and trained field service representatives. Call (800) 831-1122 for answers to your questions. Hours of operation are Monday through Thursday 8:00 am until 5:00 pm EST and on Friday 8:00 am until 4:30 pm EST.

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed. All users of the materials are responsible for assuring that it is suitable for their needs, environment and use. All data subject to change as SEM deems appropriate.

Users should review the Material Safety Data Sheet (MSDS) and product label for the material to determine possible health hazards, appropriate engineering controls and precautions to be observed in using the material. Copies of the MSDS and product label are available upon request.

SEM Products, Inc.
1685 Overview Dr. Rock Hill SC 29730
Technical Service: 800-831-1122
www.semproducts.com