Standard Operating Procedures Body Repair

Large Damage Repair



Pre-Cleaning

Pre-wash/clean vehicle prior to disassembly (power wash undercarriage area at repair).



Initial Prep Sand

DA sand the repair area using grade 80, removing paint beyond damage by 2-4 in. Blow off with clean, dry air and re-clean with surface cleaner.

Final Metal Prep

Remove remaining paint/coatings in "low spots" using a Scotch-Brite™ Clean N Strip disc. Use a 3 in. grinding disc to remove weld nuggets or other surface imperfections. Blow off with clean, dry air and re-clean with surface cleaner.



Mix and Apply Filler

Mix and apply filler per manufacturer's recommendation or use the 3M[™] Dynamic Mixing System. Keep the body filler within the primer featheredge area. Cure the body filler 15-20 minutes at 75°F.



Initial Sand Filler

Block shape sand filler with P80. DA rough featheredge area with P80 abrasive. Use 3M™ Dry Guide Coat between sanding steps to highlight imperfections. Re-apply 3M[™] Dry Guide Coat as necessary.



Final Sand Filler

Final block sand filler with P150 abrasive. DA fine featheredge sand the repair area with P180 abrasive and blow off the area with clean, dry air. Use 3M™ Dry Guide Coat between sanding steps to highlight imperfections.



Mix and Apply Glaze

Blow off the repair area completely removing sanding dust from the surface. Mix and apply glaze if required per manufacturer's recommendation or if using the 3M™ Dynamic Mixing System. Keep the glaze within the primer featheredge area. Cure glaze for 15-20 minutes at 75°F.



Sand Glaze

Block sand polyester glaze with P180 abrasive. Use 3M™ Dry Guide Coat to highlight imperfections. Re-apply glaze as necessary to fill minor imperfections.



Final Sand and Inspect

Blow off repair area. Featheredge the surrounding area using P180 abrasive. Inspect the repair for quality.

Visit www.3MCollision.com for more SOPs and videos

Product List

3M™ Car Wash Soap Concentrate, 1 gallon, PN 38377

3M™ All Purpose Cleaner and Degreaser Concentrate, 1 gallon, PN 38350

3M™ Cubitron™ II Clean Sanding Hookit[™] Abrasive Disc 3 in., 80+ grade, PN 31361; 6 in., 80+ grade, PN 31371

3M™ Platinum™ Plus Body Filler, 1 gallon, PN 01131; for DMS, PN 05863

3M™ Cubitron™ II Fibre Roloc™ Disc, 3 in., 80+ grade, PN 33392

3M™ Roloc™+ Holder, PN 07500

Scotch-Brite[™] Roloc[™]+ Clean N Strip XT Disc, PN 07470

Scotch-Brite[™] Roloc[™]+ Clean N Strip TR Disc, PN 07466

3M™ Platinum™ Plus Finishing Glaze, 30 oz., PN 31180

3M™ Platinum Glaze for DMS, 05862

3M™ Dry Guide Coat, 50 gram applicator kit, PN 05861

3M™ Cubitron™ II Hookit™ Clean Sanding Sheet Roll, 70mm x 12m, 80+ grade, PN 34442; 150+ grade, PN 34445; 180+ grade, PN 34446

3M™ Cubitron™ II Clean Sanding Hookit™ Disc, 6 in., 180+ grade, PN 31374





















Think About Your Health

3M[™] E-A-R[™] Skull Screws[™] Ear Plug, PN P1300

3M[™] Half Facepiece Respirator, PN 07182

3M™ Lexa™ Protective Eyewear, PN 15200



Protect Your Repairs

Corrosion protection is recommended for this type of repair.

Protect repairs with a self-healing, non-hardening formula

- 3M Cavity Wax Plus, PN 08852
- 3M™ Cavity Wax Plus Applicator Wand Kit, PN 08851

All OEMs recommend the application of internal anti-corrosion material during body repair, which includes cavity wax.



Individual Product Instruction and Safety Information

For individual product instructions and applicable precautions see product labels and associated literature for the individual product at **www.3MCollision.com**

For product material safety data sheets see go.3M.com/SDS

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy and Disclaimer: Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

IMPORTANT NOTE: There are of course many factors and variables that can affect an individual repair, so the technician and repair facility need to evaluate each specific application and repair process, including relevant vehicle, part and OEM guidelines, and determine what is appropriate for that repair.



3M Automotive Aftermarket Division 3M Center, Building 223-6N-01 St. Paul, MN 55144-1000 U.S.A.

3M, Accuspray, Body Schutz, Cubitron, E-A-R, Green Corps, Hookit, Lexa, Perfect-It, Platinum, PPS, Roloc, Scotch, Scotchblok, Scotch-Brite, Skull Screws, SUN GUN and Trizact are trademarks of 3M. All other trademarks are property of their respective owners.

Please recycle. Printed in U.S.A. © 3M 2016. All rights reserved. (Rev 3/2018)