TRANSTAR®
AUTOBODY TECHNOLOGIES, INC.

222

PRODUCT HIGHLIGHTS

6311
SCAT Wax & Grease Remover

DESCRIPTION:
SCAT is a specially formulated solvent blend for lifting and removing wax, silicone, grease and oil from surfaces to be painted. SCAT also provides a light etching action to improve paint adhesion. Used primarily as a pre-paint cleaner and conditioner to remove wax and silicone, SCAT leaves no residue on the surface.

PRODUCTS:
6311 SCAT Wax & Grease Remover, Gallon (3.78 L), 2/case

SURFACE PREP:
Wash application area with 6321 Speedi SCAT before sanding or grinding is done to prevent contamination from being worked into the surface.

MIX RATIO:
Ready to use.

See next page for more detailed product application. See website for this document in other languages.
Vea la página siguiente para un uso más detallado del producto. Vea el Web site para este documento en español.
Voir la prochaine page pour une application plus détaillée de produit. Voir le site Web pour ce document en français.

TRANSTAR AUTOBODY TECHNOLOGIES • 2040 HEISERMAN DRIVE, BRIGHTON, MI 48114 • (800) 824-2843
FAX (800) 477-7923 • EMAIL: info@tat-co.com

Rev 03/15

TRANSTAR®
AUTOBODY TECHNOLOGIES, INC.

222

PRODUCT DATA

6311
SCAT Wax & Grease Remover

SUITABLE SUBSTRATES:
Metal, fiberglass, plastic, painted finishes, etc.

SURFACE PREPARATION:
SCAT 6311 must be applied before sanding is done to prevent silicone or wax from being worked into the surface.

APPLICATION:
1. Saturate a clean cloth with SCAT. Work small areas rubbing briskly. Wipe off immediately with a clean, dry cloth.
2. Change cloths frequently to prevent spreading of contamination.
3. If necessary, repeat entire application until completely clean.

TECHNICAL TIPS:
For best results, wipe dry; do not let evaporate on panel.

TECHNICAL DATA:
APPEARANCE: Clear Liquid
SOLVENTS: Aliphatic and Aromatic Hydrocarbons

REGULATORY:

Category Cleaner **6311**	Individual Component
VOC Actual	6.57#/gal (788 g/l)
VOC Regulatory	6.57#/gal (788 g/l)
Weight % of Volatiles	100%
Weight % of Water	0
Weight % of Exempt Compounds	0
Volume % of Exempt Compounds	0
Density of Material	6.57

COMPETITION:
DuPont Chroma Systems 3900S/3901S
Nexa Autocolor (ICI) P850-1402
RM Diamont 905
PPG Omni MX190
Spies Hecker 7799
Matrix MX9000
5 Star PS59001
PPG Deltron/Concept DX330
Rubberseal RS609
Sikkens 5013
Montana TH5950
Martin Senour 6383
Valspar 155
U-Tech R759
Sherwin Williams R7K156
Nason 441-03
Marhyde 3224

See website (www-tat-co.com) for this document in other languages.
Vea el Web site (www.tat-co.com) para este documento en español.
Voir le site Web (www.tat-co.com) pour ce document en français.

TRANSTAR AUTOBODY TECHNOLOGIES • 2040 HEISERMAN DRIVE, BRIGHTON, MI 48114 • (800) 824-2843
FAX (800) 477-7923 • EMAIL: info@tat-co.com